Hess Grade SBS2

(Sand Blast Soft)

PARTICLE SIZE SPECIFICATION GRADE SBS2

SIZE		ALLOWABLE
MICRON	U.S. MESH	PERCENT PASSING
1400	14	100
600	30	99.7-100
425	40	47-67
300	50	3-17
250	60	0-12

TEST METHOD: ASTM C136-06

LOOSE BULK DENSITY GRADE SBS2

50 lbs/per cubic foot (ASTM C29)

CHEMICAL ANALYSIS AND PHYSICAL PROPERTIES

Chemical Name: Amorphous Aluminum Silicate

TYPICAL ANALYSIS

Silicon Dioxide: 76.2%

Aluminum Oxide: 13.5%

• Ferric Oxide: 1.1%

Ferrous Oxide: 0.1%

Sodium Oxide: 1.6%

• Potassium Oxide: 1.8%

Calcium Oxide: 0.8%

• Titanium Oxide: 0.2%

Magnesium Oxide: .05%

• Moisture: <1.0%

 Crystalline Si0₂: None Detected

GENERAL PROPERTIES

- Appearance: White powder
- · Hardness (MOHS): 6
- pH: 7.2
- Radioactivity: None
- Softening Point: 900 degrees C
- Water Soluble Substances: 0.15%
- · Loss on Ignition 5%
- GE Brightness: 84
- · Specific Gravity: 2.35
- · Reactivity: Inert

(except in the presence of calcium hydroxide or hydrofluoric acid)

ISSUE 1970 REVISION 4/2001 REVIEW 1/2008

DESCRIPTION

Amorphous (non-crystalline) in structure and composed primarily of aluminum silicate, pumice is a naturally calcined volcanic glass foam consisting of highly vesicular strands permeated with tiny air bubbles. It is these frothy, friable glass vesicles that, when carefully refined to various grades, give pumice its unique and infinitely useful qualities.

GRADE APPLICATIONS

Used for: sand blasting, metal finish texturing, non-skid paint/coatings.

PACKAGING OPTIONS

- 40 lb sacks (palleted)
- 2000 lb super sacks (palleted)
- Bulk shipped in pneumatic rail car or tractor trailer

DISTRIBUTOR NETWORK

We have stocking distributors in 23 countries on every continent except Antarctica, allowing us to deliver pumice quickly and economically worldwide.





(208) 766-4777 x111 • email: rd@hesspumice.com www.hesspumice.com

Mining and refining the purest commercial deposit of white pumice on the planet.