

Hess Grade -140 LHM

ISSUE 1993
REVISION 4/2001
REVIEW 4/2002

PARTICLE SIZE SPECIFICATION GRADE -140 LHM

SIZE		ALLOWABLE PERCENT PASSING
MICRON [MM]	U.S. MESH	
125 [0.125]	120	99.5-100
106 [0.106]	140	99-100
90 [0.09]	170	78-88
63 [0.063]	230	26-46
43 [0.043]	325	0-15

TEST METHOD: ASTM C136-06

HEAVY MINERAL GRADE -140 LHM

Heavy Mineral: ≤ 0.30

LOOSE BULK DENSITY GRADE -140 LHM

47 lb/per cubic foot [752.8 kg/per cubic meter] (ASTM C29)

CHEMICAL ANALYSIS AND PHYSICAL PROPERTIES

Chemical Name: Amorphous Aluminum Silicate

TYPICAL ANALYSIS

- Silicon Dioxide: 76.2%
- Aluminum Oxide: 13.5%
- Ferric Oxide: 1.1%
- Ferrous Oxide: 0.1%
- Sodium Oxide: 1.6%
- Potassium Oxide: 1.8%
- Calcium Oxide: 0.8%
- Titanium Oxide: 0.2%
- Magnesium Oxide: .05%
- Moisture: <1.0%
- Crystalline SiO₂: None Detected

GENERAL PROPERTIES

- Appearance: White powder
- Hardness (MOHS): 6
- pH: 7.2
- Radioactivity: None
- Softening Point: 900 degrees C
- Water Soluble Substances: 0.15%
- Loss on Ignition - 5%
- GE Brightness: 84
- Specific Gravity: 2.4
- Reactivity: Inert
(except in the presence of calcium hydroxide or hydrofluoric acid)

DESCRIPTION

Amorphous (non-crystalline) in structure and composed primarily of aluminum silicate, pumice is a naturally calcined volcanic glass foam consisting of highly vesicular strands permeated with tiny air bubbles. It is these frothy, friable glass vesicles that, when carefully refined to various grades, give pumice its unique and infinitely useful qualities.

GRADE APPLICATIONS

Used for: Glass grinding, polishing

PACKAGING OPTIONS

- 1 lb or 1 kg resealable bags
- 42 lb [19 kg] bags (palletted)
- 44 lb [20 kg] bags (palletted)
- 1323 to 1800 lb [600 / 816 kg] super sacks (palletted)
- Bulk shipped in rail car or tractor trailer

DISTRIBUTOR NETWORK

We have stocking distributors in 23 countries on every continent except Antarctica, allowing us to deliver pumice quickly and economically worldwide.

