# SoilRox<sup>™</sup> Blender SF

# **PARTICLE SIZE SPECIFICATION BLENDER SF**

SIZE			ALLOWABLE
MICRON	MM	U.S. MESH	PERCENT PASSING
9525	9.5	3/8	98-100
4750	4.75	4	30-75
2380	2.38	8	0-20
300	0.3	50	0-12
150	0.15	100	0-10
TECT METHOD, ACTM C13C OC			

TEST METHOD: ASTM C136-06

# **LOOSE BULK DENSITY SOILROX BLENDER SF**

**60** lb/per cubic foot (damp) [**961** kg/per cubic meter] (ASTM C29)





**LEFT**: SoilRox Blender SF contains some fines. The fines enhance moisture and nutrient retention on a micro level at a more complete in-soil dispersion rate while the larger stones enhance the aeration profile and faciliate drainage. **RIGHT**: Soil Rox Blender SF is a lightweight, multiple-benefit component in containerized, engineered-soil growing applications.



(208) 766-4777 • www.hesspumice.com

Mining and refining the purest commercial deposit of white pumice on the planet.



# **PACKAGING OPTIONS**

- 2.5 lb [1.1 kg] resealable bag
- 20 lb [9 kg] box
- 45 lb [20.4 kg] production bag
- 2000 lb [907 kg] super sacks (palleted)
- Bulk shipped in rail car or tractor trailer

## **ORDER**

- Samples, small quantities: order direct from the PumiceStore.com
- Palleted super sacks, truckloads: contact us at sales@hesspumice.com or call 208-766-4777

### **PUMICE TECHNICAL DATA**

Chemical analysis, physical properties, and other common data shared by all Hess Pumice grades are detailed on back.

# Hess Pumice Technical Data

# **CHEMICAL ANALYSIS** AND **PHYSICAL PROPERTIES**

Chemical Name: Amorphous Aluminum Silicate

# TYPICAL ANALYSIS

- Silicon Dioxide: 76.2%
- Aluminum Oxide: 13.5%
- Ferric Oxide: 1.1%
- Ferrous Oxide: 0.1%
- Sodium Oxide: 1.6%
- Potassium Oxide: 1.8%
- Calcium Oxide: 0.8%
- Titanium Oxide: 0.2%
- Magnesium Oxide: .05%
- Moisture: <1.0%</li>
- Crystalline Si0<sub>2</sub>: None Detected

### **GENERAL PROPERTIES**

- Appearance: White powder
- Hardness (MOHS): 6
- pH: 7.2
- Radioactivity: None
- Softening Point: 900 degrees C
- Water Soluble Substances: 0.15%
- · Loss on Ignition 5%
- GE Brightness: 84
- Specific Gravity: 2.2
- Reactivity: Inert

(except in the presence of calcium hydroxide or hydrofluoric acid)

# Pumice is a foamed glass stone naturally expanded by explosive volcanic eruption.

### DESCRIPTION

Amorphous (non-crystalline) in structure and composed primarily of aluminum silicate, pumice is a naturally calcined volcanic glass foam consisting of highly vesicular strands permeated with tiny air bubbles. It is these frothy, friable glass vesicles that, when carefully refined to various grades, give pumice its unique and infinitely useful qualities.

### **NOTES**

- Chemical analysis and physical properties provided are common to all raw Hess pumice grades.
- Grade Variety. The natural, hardyet-friable character of our pumice combined with our crushing and screening expertise allow us to offer pumice grades and grade blends down to 3 microns.
- Safe to Use. No hazardous crystalline structure: testing for crystalline silica (airborne particles of respirable size) finds no measurable Crystalline Silica (SiO<sub>2</sub>) present. Free of heavy metals, pesticides, nano-particles, allergens. Certified organic input material.
- Purity: As the result of centuries of wave action from a now-extinct inland sea, our pumice is remarkably pure. Our mine grades are typically comprised of 98% pumice and 2% other igneous minerals, which are not removed through our mining processes.
- Storage: Keep dry and protected from the elements until use.



(208) 766-4777 www.**hesspumice.com**